

Theory of Elasticity

Contents

- *Definition of Elastic Constants*
- *Calculation of Elastic Constants*
- *Polycrystalline Materials: Voigt-Reuss-Hill Method*
- *Thermal Expansion and Heat Capacity*
- *Isotropic Systems*
- *Elastic Constants for Disordered Cubic Systems*
- *Hashin-Shtrikman bounds for cubic systems*
- *Hill-Walpole Bounds for Amorphous Systems*

1 Definition of Elastic Constants

To determine the elastic constants of a crystal, a deformation of the unit cell is created by changing the Bravais lattice vectors $R = (a, b, c)$ of the undisturbed unit cell to $R' = (a', b', c')$ using an engineering strain matrix e

$$R' = R \begin{pmatrix} 1 + e_{xx} & \frac{1}{2}e_{xy} & \frac{1}{2}e_{xz} \\ \frac{1}{2}e_{yx} & 1 + e_{yy} & \frac{1}{2}e_{yz} \\ \frac{1}{2}e_{zx} & \frac{1}{2}e_{zy} & 1 + e_{zz} \end{pmatrix} \quad (1)$$

The deformation leads to a change of the total energy of the crystal

$$U = \frac{E_{tot} - E_0}{V_0} = \frac{1}{2} \sum_{i=1}^6 \sum_{j=1}^6 C_{ij} e_i e_j$$

where E_0 is the total energy of the unstrained lattice, V_0 is the volume of the undistorted cell and the C_{ij} are the elements of the **elastic constant matrix** with a notation that follows standard convention.

Both i and j run from 1...6 in the sequence $\{xx, yy, zz, yz, xz, xy\}$. The tensor of elasticity has 36 elements, the elastic constants, but maximally 21 of these are independent. The symmetry of the unit cell can reduce the number of independent elastic constants for the various symmetry systems as shown in the following table:

Table1: Number of independent elastic constants for unit cells of different symmetry

CRYSTAL SYSTEM	ELASTIC CONSTANTS
Triclinic	21
Monoclinic	13
Orthorhombic	9
Tetragonal	6 or 7
Rhombohedral	6 or 7
Hexagonal	5
Cubic	3

2 Calculation of Elastic Constants

The simplest case by far is the cubic system where there are only three independent constants, C_{12} , C_{11} , and C_{44} . We use this case to illustrate the manner in which the stiffness matrix elements may be determined from strain fields of the form of Eq. (1). If the applied engineering strain is $e_{xx} = e$ with all other e_{ij} equal to zero, the energy change is $U = C_{11} \frac{e^2}{2}$. This allows a unique determination of C_{11} . If $e_{yz} = e_{zy} = \frac{e}{2}$, with all other strain components zero, then $U = C_{44} \frac{e^2}{2}$ and we have an independent determination of C_{44} . The bulk modulus, B , is the response to a uniform compression so applying the strain field $e_{xx} = e_{yy} = e_{zz} = e$ allows the computation of B via the relation $U = \frac{B e^2}{2}$. Similarly, the shear modulus can be calculated by using the strain field $e_{zz} = e$; $e_{xx} = e_{yy} = -\frac{e}{2}$, whereupon $U = 3C' \frac{e^2}{2}$. Finally, the off-diagonal stiffness matrix element C_{12} can be calculated using one or other of the relations

$$B = \frac{1}{3}(C_{11} + 2C_{12})$$

$$C' = \frac{1}{2}(C_{11} - C_{12})$$

Using both of these relations provides a useful independent check on the accuracy of the computation. A symmetry-general formulation of the calculation of elastic constants from total energy calculations is given by Le Page & Saxe [1].

2.1 Computational Aspects

The current implementation in *MedeA* is based on stress [2]. Vasp calculates the stress tensor, *i.e.* the derivatives of the total energy of the cell with respect to changes of the 6 lattice parameters (cell lengths and angles), using analytic expressions. With a single value for the amount of distortion for each of the necessary engineering strains, it is possible to obtain the elastic constants. For simplicity, the amount of distortion is called "strain" in the Vasp interface. A good value for the strain is 2%. If this value is too small the changes in the stress may be too small for accurate tracking. If e is too large, anharmonicity of the energy may play a role. Several strains can be used to get more points for the fitting procedure involved in the calculation of the elastic constants, thus leading to a higher numerical stability.

Hint: The elastic constants can be calculated for the equilibrium structure (at zero pressure) of a crystal, which is the usual case, or for distorted lattices. To ensure that the equilibrium structure does correspond to zero strain, the initial optimization of the theoretical cell parameters must be made with extremely high accuracy. In particular, for metallic systems a fine k-mesh (k-spacing of about $0.2/\text{\AA}$) and the tetrahedron integration scheme should be used. The geometry convergence criterion should be $0.01 \text{ eV}/\text{\AA}$ and the SCF convergence criterion needs to be set at $1.0\text{E-}06$ or $1.0\text{E-}07$.

Experimental values for the lattice constants, even where these are available, should not be used because the *theoretical* lattice will be in a state of strain for these values. This is because in the first instance, theory, and experiment will not agree exactly and in the second, the experimental error is unknown and probably of the same order as the strain field one needs to apply.

3 Polycrystalline Materials: Voigt-Reuss-Hill Method

The stiffness matrix calculated as above refers to the perfect lattice. However, approximate values referring to polycrystalline samples that take into account orientational disorder can be estimated from the single crystal data if one assumes that the elastic behavior is determined by the individual crystallites and not grain

[1] Y Le Page and Paul Saxe, "Symmetry-General Least-Squares Extraction of Elastic Coefficients From Ab Initio Total Energy Calculations," *Physical Review B* 63, no. 17 (March 2001): 174103.

[2] Yvon Le Page and Paul Saxe, "Symmetry-General Least-Squares Extraction of Elastic Data for Strained Materials From Ab Initio Calculations of Stress," *Physical Review B* 65 (2002): 104104.

boundary effects. A thorough analysis of this issue can be found in a paper by Anderson [3]. The basic method, the Voigt-Reuss-Hill method, devolves from the expression for the shear modulus, G ,

$$G_{Hill} = \frac{1}{2} [G_{Voigt} + G_{Reuss}] \quad (2)$$

For cubic lattices, the Voigt and Reuss approximations for the shear modulus, G_{Voigt} and G_{Reuss} , are:

$$G_{Voigt} = \frac{1}{5} (C_{11} - C_{12} + 3C_{44}) \quad (3)$$

and

$$G_{Reuss} = \frac{5}{4(S_{11} - S_{12}) + 3S_{44}} \quad (4)$$

where S is the compliance matrix (i.e. the inverse matrix to C and that therefore the arithmetic mean should give a better estimate of G than either approximation. Checks by Anderson showed this to be true. Since the bulk moduli of the perfect crystal and a mono-phase polycrystal are the same, elastic data for the polycrystalline phase amount just to using the shear modulus as given by (2), (3), (4) in place of the value for the perfect crystal.

Once B and G are determined, Poisson's ratio, σ , and Young's modulus, Y , are given by the standard formulae of elasticity

$$\sigma = \frac{1}{2} \frac{B - \frac{2}{3}G}{2B + \frac{1}{3}G}$$

and

$$Y = \frac{9B}{1 + \frac{3B}{G}}$$

Correspondingly, the mean values for the transverse and longitudinal sound velocities v_t and v_l are given in terms of the elastic moduli and the mean density ρ by

$$v_t = \sqrt{\frac{G}{\rho}}$$

and

$$v_l = \sqrt{\frac{B + \frac{4}{3}G}{\rho}}$$

Finally, the mean sound velocity v_m is

$$v_m = \left(\frac{1}{3} \left(\frac{2}{v_t^3} + \frac{1}{v_l^3} \right) \right)^{-1/3}$$

4 Thermal Expansion and Heat Capacity

In the discussion in the previous sections, temperature played no role and the computation of the elastic constants referred to zero temperature. For a harmonic lattice, as is well known, the mean lattice parameters and elastic constants are independent of temperature. The observed temperature dependence of these quantities devolves from *anharmonic* behavior of the energy, which is why the computation of the coefficient

[3] Orson L Anderson, "A Simplified Method for Calculating the Debye Temperature From Elastic Constants," Journal of Physics and Chemistry of Solids 24, no. 7 (1963): 909-917.

of thermal expansion is one degree more difficult than the computation of the zero temperature elastic constants. The foundation for the computation of thermal corrections to lattice parameters was laid down by Grüneisen [4], remarkably, before the widespread acceptance of quantum mechanics! Of course, Grüneisen could only write down formulae. Even the simplest computation was beyond the capacity of hand calculators. Today, however, it is possible to implement Grüneisen's work, again using DFT as a generator of energies and forces, and the results can be very spectacular.

The full implementation of Grüneisen's theory requires evaluation of the material's phonon spectra and the derivatives of the individual phonon frequencies with respect to the cell parameters. However, there is a lower level of theory, the Grüneisen-Debye approximation, that allows computation of the thermal expansion coefficient with essentially no more effort than the elastic constants. In fact, for a cubic material, the only additional information to the elastic constants that is required is an averaged Grüneisen constant, γ_G . As a first step, which is implemented, the Grüneisen constant is set to 2. The next step, which is planned, is the determination of γ_G from the pressure-volume, or internal energy-volume equation of state. A convenient approximation that incorporates γ_G as a parameter is [5]

$$E(V) = \frac{BV_0}{\frac{5}{6} - \gamma_G} \left(\frac{V}{V_0} \right)^{\frac{5}{6} - \gamma_G} \left(\ln \frac{V}{V_0} - \frac{1}{\frac{5}{6} - \gamma_G} \right) + E_{\text{inf}}$$

where V_0 is the equilibrium volume. Since γ_G is essentially the third derivative of $E(V)$, the computation of this function must be carried out with high accuracy and great care. This can, however, be done.

Once γ_G is obtained, the only other input required to compute the thermal expansion coefficient is the Debye temperature, which is determined by exploiting its relationship to the sound velocity *i.e.*

$$\theta_D = \frac{\hbar}{k_B} \left(\frac{6\pi^2 q}{V_0} \right)^{\frac{1}{3}} v_m$$

where q is the number of atoms in the unit cell, V_0 its volume, and \hbar and k_B are the Planck and Boltzmann constants, respectively. The lattice contribution to the specific heat capacity, C_V , as a function of temperature, T , can then be calculated via (see, for example, Mayer [5])

$$C_V(T) = 9qk_B \left(\frac{T}{\theta_D} \right)^3 \int_0^{x_D} x^4 \frac{\exp x}{(\exp x - 1)^2} dx$$

where $X_D = \frac{\theta_D}{T}$ and the linear thermal expansion coefficient α_L is given via the standard relation [6]

$$\alpha_L(T) = \frac{1}{3} \gamma_G \frac{C_V(T)}{BV_0}$$

5 Isotropic Systems

In the isotropic regime, there are only two independent moduli and we can express e.g. the Young modulus E can be expressed from Bulk K , Shear G modulus, Poisson ratio ν , Lamé's first coefficient λ or P-wave modulus M with the various relationships from below:

[4] Eduard Grüneisen, "Zustand Des Festen Körpers," in Thermische Eigenschaften Der Stoffe. Handbuch Der Physik, (Springer Berlin / Heidelberg, 1928), 1.

[5] B Mayer, H Anton, E Bott, M Methfessel, J Sticht, et al., "Ab-Initio Calculation of the Elastic Constants and Thermal Expansion Coefficients of Laves Phases," Intermetallics 11, no. 1 (2003): 23-32.

[6] NW Ashcroft and ND Mermin, Solid State Physics, Holt-Saunders, 1976.

	(K,E)	(K,λ)	(K,G)	(K,ν)	(E,G)	(E,ν)	(λ,G)	(λ,ν)	(G,ν)	(G,M)
K=					$\frac{EG}{3(3G-E)}$	$\frac{E}{3(1-2\nu)}$	$\lambda + \frac{2G}{3}$	$\frac{\lambda(1+\nu)}{3\nu}$	$\frac{2G(1+\nu)}{3(1-2\nu)}$	$M - \frac{4G}{3}$
E=	$\frac{9K(K-\lambda)}{3K-\lambda}$	$\frac{9KG}{3K+G}$	$3K(1-2\nu)$				$\frac{G(3\lambda+2G)}{\lambda+G}$	$\frac{\lambda(1+\nu)(1-2\nu)}{\nu}$	$2G(1+\nu)$	$\frac{G(3M-4G)}{M-G}$
λ=	$\frac{3K(3K-E)}{9K-E}$	$K - \frac{2G}{3}$	$\frac{3K\nu}{1+\nu}$	$\frac{G(E-2G)}{3G-E}$	$\frac{E\nu}{(1+\nu)(1-2\nu)}$				$\frac{2G\nu}{1-2\nu}$	$M-2G$
G=	$\frac{3KE}{9K-E}$	$\frac{3(K-\lambda)}{2}$	$\frac{3K(1-2\nu)}{2(1+\nu)}$		$\frac{E}{2(1+\nu)}$			$\frac{\lambda(1-2\nu)}{2\nu}$		
ν=	$\frac{3K-E}{6K}$	$\frac{\lambda}{3K-\lambda}$	$\frac{3K-2G}{2(3K+G)}$	$\frac{E}{2G} - 1$			$\frac{\lambda}{2(\lambda+G)}$			$\frac{M-2G}{2M-2G}$
M=	$\frac{3K(3K+E)}{9K-E}$	$3K-2\lambda$	$K + \frac{4G}{3}$	$\frac{3K(1-\nu)}{1+\nu}$	$\frac{G(4G-E)}{3G-E}$	$\frac{E(1-\nu)}{(1+\nu)(1-2\nu)}$	$\lambda+2G$	$\frac{\lambda(1-\nu)}{\nu}$	$\frac{2G(1-\nu)}{1-2\nu}$	

The relationship between moduli and to elastic and compliance matrices is simple:

$$C_{11} = M, \quad C_{12} = \lambda, \quad C_{44} = G \quad \text{and} \quad S_{11} = \frac{1}{E}, \quad S_{12} = \frac{\nu}{E}, \quad S_{44} = \frac{1}{G}$$

6 Elastic Constants for Disordered Cubic Systems

When reporting elastic data for a disordered structure, one can take inspiration from the averaging by Voigt and Reuss and “effective” coefficients for a simplified, anisotropic cubic system:

$$\begin{aligned} \overline{C_{11}} &= \frac{C_{11} + C_{22} + C_{33}}{3} & \overline{S_{11}} &= \frac{S_{11} + S_{22} + S_{33}}{3} \\ \overline{C_{12}} &= \frac{C_{23} + C_{13} + C_{12}}{3} & \overline{S_{12}} &= \frac{S_{23} + S_{13} + S_{12}}{3} \\ \overline{C_{44}} &= \frac{C_{44} + C_{55} + C_{66}}{3} & \overline{S_{44}} &= \frac{S_{44} + S_{55} + S_{66}}{3} \end{aligned}$$

This averaging is justified, as we can recreate the two matrices (in the simple anisotropic, cubic case) from the polycrystalline moduli and the Zener anisotropy ratio A , which is independent of whether Voigt or Reuss averaging is chosen.

$$\begin{aligned} K_V &= \frac{\overline{C_{11}} + 2\overline{C_{12}}}{3} & K_R &= \frac{1}{3\overline{s_{11}} + 6\overline{s_{12}}} \\ G_V &= \frac{\overline{C_{11}} - \overline{C_{12}} + 3\overline{C_{44}}}{5} & G_R &= \frac{5}{4\overline{s_{11}} - 4\overline{s_{12}} + 3\overline{s_{44}}} \end{aligned}$$

And back from Moduli to elastic matrix and compliance

$$\begin{aligned} C_{11} &= K + \frac{10}{3G_V} - \frac{10G_V}{2A+3} & S_{11} &= \frac{1}{9K_R} + \frac{6}{5G_R} - \frac{5A}{2G_R(2+3A)} \\ C_{12} &= K - \frac{3G_V}{5} - \frac{2A+3}{5G_V} & S_{12} &= \frac{1}{9K_R} - \frac{12G_R}{5A} + \frac{4G_R(2+3A)}{5A} \\ C_{44} &= \frac{5G_V}{2A+3} & S_{44} &= \frac{1}{G_R(2+3A)} \end{aligned}$$

7 Hashin-Shtrikman bounds for cubic systems

Voigt [7] (1928) averaged the elastic stiffnesses (C_{ij}) over all space. Reuss [8] (1929) averaged the elastic compliances (S_{ij}). Hill [9] (1952) showed that these averaged values are the least upper bound and the greatest lower bound, respectively for the aggregate.

[7] Woldemar Voigt, Lehrbuch Der Kristallphysik (Mit Ausschluss Der Kristalloptik), (Leipzig: Teubner, 1928).

[8] A Reuss, “Berechnung Der Fließgrenze Von Mischkristallen Auf Grund Der Plastizitätsbedingung Für Einkristalle,” ZAMM - Zeitschrift Für Angewandte Mathematik Und Mechanik 9, no. 1 (1929): 49-58.

[9] R Hill, “The Elastic Behaviour of a Crystalline Aggregate,” Proceedings of the Physical Society. Section A 65, no. 5 (May 1, 1952): 349-354.

The Voigt and Reuss averages are given by:

$$\begin{aligned}
 \bar{C}_{11} &= \frac{C_{11} + C_{22} + C_{33}}{3} & \bar{S}_{11} &= \frac{S_{11} + S_{22} + S_{33}}{3} \\
 \bar{C}_{12} &= \frac{C_{23} + C_{13} + C_{12}}{3} & \bar{S}_{12} &= \frac{S_{23} + S_{13} + S_{12}}{3} \\
 \bar{C}_{44} &= \frac{C_{44} + C_{55} + C_{66}}{3} & \bar{S}_{44} &= \frac{S_{44} + S_{55} + S_{66}}{3} \\
 K_V &= \frac{\bar{C}_{11} + 2\bar{C}_{12}}{3} & K_R &= \frac{1}{3\bar{S}_{11} + 6\bar{S}_{12}} \\
 G_V &= \frac{\bar{C}_{11} - \bar{C}_{12} + 3\bar{C}_{44}}{5} & G_R &= \frac{5}{4\bar{S}_{11} - 4\bar{S}_{12} + 3\bar{S}_{44}}
 \end{aligned}$$

Hashin and Shtrikman [10] showed that the Voigt and Reuss bounds could be improved, and they developed expressions for the corresponding bounds of aggregates of cubic crystals. As it turns out, the difference between the upper and lower bounds for cubic crystals is improved by at least an order of magnitude for most materials. For a single-phase aggregate of a cubic material, the bulk modulus, K , is given unambiguously by

$$K = \frac{1}{3}(\bar{C}_1 + 2\bar{C}_{12})$$

And the rigidity is bounded by

$$\begin{aligned}
 G_1^* &= G_1 + \frac{3}{\frac{5}{G_2 - G_1} - 4\beta_1} & G_2^* &= G_2 + \frac{2}{\frac{5}{G_1 - G_2} - 6\beta_2} \\
 G_1 &= \frac{1}{2}(C_{11} - C_{12}) & G_2 &= C_{44} \\
 \beta_1 &= -\frac{3(K + 2G_1)}{5G_1(3K + 4G_1)} & \beta_2 &= -\frac{3(K + 2G_2)}{5G_2(3K + 4G_2)} \\
 &= -\frac{2}{15} \frac{4C_{11} - C_{12}}{C_{11}(C_{11} - C_{12})} & &= -\frac{C_{11} + 2C_{12} + 6C_{44}}{5C_{44}(C_{11} + 2C_{12} + 4C_{44})}
 \end{aligned}$$

The factors G_1 and G_2 are no coincidence, remember that in isotropic elasticity, the shear modulus $G = C_{44}$, which turns up here as G_2 . The same ingredients appear in Zener's anisotropy coefficient A , which can be written as

$$A = \frac{G_2}{G_1} = \frac{2C_{44}}{C_{11} - C_{12}}$$

This also determines which of the two values is the upper and lower bound:

$$\begin{aligned}
 A < 1 : & \quad G_H = G_1^* & G_S &= G_2^* \\
 A = 0 : & \quad G_H = G_S = G_{Hill} \\
 A > 1 : & \quad G_H = G_2^* & G_S &= G_1^*
 \end{aligned}$$

The larger term of G_1^* and G_2^* is termed the Hashin rigidity, G_S , the smaller Shtrikman rigidity, G_H . These two are much closer to each other than Voigt and Reuss bounds in equation

$$C_V = \frac{\bar{C}_{11} - 2\bar{C}_{12} + 3\bar{C}_{44}}{5} > G_H > G_{Hill} > G_S > G_R = \frac{5}{4\bar{S}_{11} - 4\bar{S}_{12} + 3\bar{S}_{44}}$$

[10] Z Hashin and S Shtrikman, "On Some Variational Principles in Anisotropic and Nonhomogeneous Elasticity," Journal of the Mechanics and Physics of Solids 10, no. 4 (October 1962): 335-342; Z Hashin and S Shtrikman, "A Variational Approach to the Theory of the Elastic Behaviour of Polycrystals," Journal of the Mechanics and Physics of Solids 10, no. 4 (October 1962): 343-352.

8 Hill-Walpole Bounds for Amorphous Systems

Atomistic simulations of amorphous glassy materials are typically performed using periodic cells with lateral dimensions of no more than a few tens of Angstroms. Moreover, to model accurately and to predict the expected macroscopic properties of a given material it will often be necessary to sample many distinct realizations (i.e. cells), each differing in local packing of atoms. In the case of mechanical properties, computed 6x6 matrices of stiffness or compliance constants may differ quite considerably between cells and each may be slightly anisotropic, even when the parent material is homogeneous and perfectly isotropic.

An important question confronting modelers seeking to predict mechanical properties and often to quantify differences between materials, concerns how to combine elastic constants obtained for nanoscopic regions represented by amorphous cells to define the macroscopic elastic constants as precisely as possible. Instinctively, the basic approach involves viewing the macroscopic material as a composite made up of many distinct domains - i.e. individual cells - embedded in a matrix formed by all other cells.

As well-established in composite theory, the extreme upper and lower bounds of the elastic constants can then be determined by computing averages of the individual stiffness and compliance matrices. These are the so-called Voigt and Reuss bounds, which are obtained by assuming that each individual domain is subjected to the same strain or the same stress respectively.

$$\langle C \rangle_{Voigt} = \frac{1}{n} \sum_i C_i \quad \text{and} \quad \langle S \rangle_{Reuss} = \frac{1}{n} \sum_i S_i$$

Since in reality neither assumption is rigorously true, these represent extreme bounds, as the forces between domains in the Voigt average cannot be in equilibrium; likewise the distorted domains in the Reuss average cannot fit together. It is just the most simplistic estimate of the likely macroscopic properties, though it has been suggested that simply taking the mid-point of the bounds interval can sometimes provide useful estimates of the material elastic constants.

In the case of amorphous glassy materials as frequently modeled by a collection of cells containing a few thousand to a few tens of thousands of atoms, where lateral dimensions range from around 20 to 50 Angstroms, upper and lower bounds calculated in this way typically show large differences. With the goal of improving the reliability of predictions of the elastic constants of macroscopic samples of material, Suter and Eichinger [11] accordingly investigated the possibility of obtaining refined bounds estimates from raw 'amorphous cell' elastic constant data.

By again proceeding with the analogy with composite models, and taking the view that each domain can be considered as being embedded within a homogeneous continuum with elastic properties equal to the average material, these authors applied theory developed earlier by Hill [12] and by Walpole [13] to compute improved and typically much narrower bounds estimates.

Suter and Eichinger then proceeded to investigate the effectiveness of the approach at 'predicting' the elastic constants of amorphous glassy polystyrene using input data 'synthesized' by adding random fluctuations to actual experimental stiffness coefficients, where the random fluctuations were chosen based on those observed in typical atomistic simulations. The results essentially demonstrated that the range of the computed new 'Hill-Walpole' bounds was significantly smaller than the difference of the Voigt-Reuss averages, and consistently closer to the known values used to generate the input data than the midpoint of the Voigt-Reuss range.

[11] U W Suter and Bruce E Eichinger, "Estimating Elastic Constants by Averaging Over Simulated Structures," *Polymer* 43, no. 2 (January 2002): 575-582.

[12] R Hill, "A Self-Consistent Mechanics of Composite Materials," *Journal of the Mechanics and Physics of Solids* 13, no. 4 (August 1965): 213-222; R Hill, "Continuum Micro-Mechanics of Elastoplastic Polycrystals," *Journal of the Mechanics and Physics of Solids* 13, no. 2 (April 1965): 89-101.

[13] L J Walpole, "On Bounds for the Overall Elastic Moduli of Inhomogeneous Systems-I," *Journal of the Mechanics and Physics of Solids* 14, no. 3 (May 1966): 151-162; L J Walpole, "On the Overall Elastic Moduli of Composite Materials," *Journal of the Mechanics and Physics of Solids* 17, no. 4 (September 1969): 235-251.